

Assistant Commissioner for Patents Washington, DC 20231 ATTN: BOX UTILITY APPLICATION

Sheet 1 of 2

UTILITY PATENT APPLICATION TRANSMITTAL

Docket No.: 00-508 Date: November 8, 2000



	U.S. I	Express Mail Label No	: EL661474385US			
CHRI	or Nam STOPH G F. HA	ER L. AARDAHL; MAI	RI LOU BALMER; ASHOK (NMI) CHANDA; SHKARIAN; AND PAUL W. PARK			
PLAS	MA AN	ID METAL/METAL OX	COMBINATION OF NON-THERMAL IDE DOPED Y -ALUMINA CATALYSTS FOR RTREATMENT SYSTEM			
X	Fee T	ransmittal Form Attacl	ned in Duplicate			
X	Specif	fication and Claim(s)	[Total Pages 27]			
X	Drawi	ng(s)	[Total Sheets 8]			
	INFO	ORMAL				
Declar	ation		[Total Pages]			
		Newly Executed (Ori	ginal or Copy)			
		Copy From Prior App	plication (37 CFR § 1.63(d))			
			ventor(s) (37 CFR § 1.63(d)(2)) ment Attached)			
	Assign	nment Papers (Cover S	heet and Document(s))			
	37 CFR § 3.73(b) Statement (if applicable)					
	English Translation Document (if applicable)					
	Information Disclosure Statement (IDS)/PTO-1449					
		Copies of IDS Citatio	ns			
	Prelim	inary Amendment				
X	Return Receipt Postcard (Specifically Itemized)					
	Certified Copy of Priority Document(s)					
	Other					

If a Continuing Application									
☐ Co	☐ Continuation ☐ Divisional ☐ Continuation-In-Part (Continuation)								
of prior Application No.:									
Examiner: ; and									
Group	/Art Unit:								
□ Ca	application, from which a	n oath or declaration is si isclosure of the accompa	: The entire disclosure of the applied, as set forth above, is aying continuation or division e.	_					
Corres	pondence Address:								
X	Customer Number or	Bar Code Label:	719						
	or								
	Correspondence addre	ess below:							
	Name:								
	Address:								
	City:	State:	Zip Code:						
	Country:								

Attorney/Agent: O. Gordon Pence Registration No.: 27,669 Signature: Date: 11/8/00 Caterpillar Inc.									

FEE	TR	AN	SMIT	TAL
=	for	FY	2000	

Patent fees are subject to annual revision. Small Entity payments must be supported by a small entity statement, otherwise large entity fees must be paid. See Forms PTO/SB/09-12. See 37 C.F.R. §§ 1.27 and 1.28.

TOTAL AMOUNT OF PAYMENT

7	7	o
•	_	v

(\$)

Complete if Known					
Application Number	(Unassigned)				
Filing Date	(Herewith)				
First Named Inventor	CHRISTOPHER L. AARDAHL ET AL.				
Examiner Name	(Unassigned)				
Group / Art Unit	(Unassigned)				
Attorney Docket No.	00-508				

METHOD OF PAYMENT (check one)	FEE CALCULATION (continued)				
The Commissioner is hereby authorized to charge indicated fees and credit any overpayments to: Deposit	3. ADDITIONAL FEES Large Entity Small Entity Fee	Fee Paid			
Account Number 03-1129	Code (\$) Code (\$) 105 130 205 65 Surcharge - late filing fee or oath				
Deposit	127 50 227 25 Surcharge - late provisional filing fee or				
Account Name	cover sheet.				
Charge Any Additional Fee Required	139 130 139 130 Non-English specification 147 2.520 147 2.520 For filing a request for reexamination				
Under 37 CFR §§ 1.16 and 1.17	147 2,520 147 2,520 For filing a request for reexamination 112 920* 112 920* Requesting publication of SIR prior to	-			
2. Payment Enclosed:	Examiner action				
Check Money Other	113 1,840* 113 1,840* Requesting publication of SIR after Examiner action				
FEE CALCULATION	115 110 215 55 Extension for reply within first month				
1. BASIC FILING FEE	116 380 216 190 Extension for reply within second month				
Large Entity Small Entity	117 870 217 435 Extension for reply within third month				
Fee Fee Fee Fee Description	118 1,360 218 680 Extension for reply within fourth month				
Code (\$) Code (\$) Fee Paid 101 690 201 345 Utility filing fee	128 1,850 228 925 Extension for reply within fifth month				
710	119 300 219 150 Notice of Appeal				
106 310 206 155 Design filling fee	120 300 220 150 Filing a brief in support of an appeal				
107 480 207 240 Plant filing fee	121 260 221 130 Request for oral hearing				
108 690 208 345 Reissue filing fee	138 1,510 138 1,510 Petition to institute a public use proceeding				
114 150 214 75 Provisional filing fee	140 110 240 55 Petition to revive - unavoidable				
SUBTOTAL (1) (\$) 710	141 1,210 241 605 Petition to revive - unintentional				
2. EXTRA CLAIM FEES	142 1,210 242 605 Utility issue fee (or reissue)				
Fee from Ext <u>ra Claims below</u> Fee Paid	143 430 243 215 Design issue fee				
Total Claims 20 -20** = 0 x 18 = 0	144 580 244 290 Plant issue fee				
Independent 2 - 3** = 0 x 80 = 0	122 130 122 130 Petitions to the Commissioner				
Multiple Dependent	123 50 123 50 Petitions related to provisional applications				
**or number previously paid, if greater; For Reissues, see below Large EntitySmall Entity	126 240 126 240 Submission of Information Disclosure Stmt				
Fee Fee Fee Fee Fee Description Code (\$) Code (\$)	581 40 581 40 Recording each patent assignment per property (times number of properties)				
103 18 203 9 Claims in excess of 20	146 690 246 345 Filing a submission after final rejection (37 CFR § 1.129(a))				
102 78 202 39 Independent claims in excess of 3 104 260 204 130 Multiple dependent claim, if not paid	149 690 249 345 For each additional invention to be				
109 78 209 39 ** Reissue independent claims over original patent	examined (37 CFR § 1.129(b)) Other fee (specify)				
110 18 210 9 ** Reissue claims in excess of 20 and over original patent	Other fee (specify)				
SUBTOTAL (2) (\$) 0	Reduced by Basic Filing Fee Paid SUBTOTAL (3)	0			
SUBMITTED BY	Complete (if applicable)				
Name (Print/Type) O. Gordon Bence	Registration No. 27 CCO Tolophoro	75-4460			
Signature / Sorden Alex					

Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

Description

METHOD AND SYSTEM FOR THE COMBINATION OF NON-THERMAL PLASMA AND METAL/METAL OXIDE DOPED Y-ALUMINA CATALYSTS FOR DIESEL ENGINE EXHAUST AFTERTREATMENT SYSTEM

This invention was made with Government support under DOE Contract No. DE-AC06-76RLO 1830 awarded by the U.S. Department of Energy. The Government has certain rights to this invention.

Technical Field

This invention relates generally to a system and method for treatment of lean exhaust, such as diesel exhaust and lean burn gasoline engine exhaust, to reduce nitrogen oxide (NO $_x$) emissions and more specifically to a method and system that combines non-thermal plasma with a metal doped Y-alumina catalyst for NO $_x$ reduction.

20

25

30

5

10

15

Background Art

The catalytic converters, especially three-way catalysts, used in combination with modern gasoline engines have resulted in a great reduction in tailpipe emissions of carbon monoxide, hydrocarbons and NO_x . There is an increasing emphasis on fuel efficiency and diesel engines have an efficiency advantage over gasoline engines. Unfortunately, diesel engines are "lean burn" engines and their exhaust has very high levels of oxygen. These high levels of oxygen render gasoline catalytic converters useless for NO_x reduction. Catalysts or catalytic

systems that have been utilized for lean burn engines to date suffer from low removal of NO_x , low thermal stability and a limited temperature window of operation. Most current catalytic systems for lean burn engines only achieve 7-12% NO_x reduction as a passive system and 25-40% when supplemental hydrocarbon reductant is injected into the exhaust stream. Use of a non-thermal plasma system for reduction of NO_x in conjunction with a particulate trap is disclosed in U.S. Patent No. 6,038,854 issued March 21, 2000 to Penetrante et al.

The present invention is directed to overcome one or more of the problems as set forth above.

15

25

30

10

Disclosure of the Invention

In one aspect of this invention, there is disclosed a method for nitrogen oxide (NO $_{\rm x}$) reduction in an oxygen rich engine exhaust comprising the steps of passing an oxygen rich exhaust through a nonthermal plasma thereby converting nitrogen oxide (NO) and hydrocarbons in the oxygen rich exhaust into nitrogen dioxide (NO $_{\rm 2}$) and oxidized hydrocarbons and forming an intermediate exhaust; and then passing the intermediate exhaust over at least one metal doped Y-alumina, wherein the Y-alumina has been prepared with a pore volume of greater than 1.0 cubic centimeters per gram, thereby converting the NO $_{\rm 2}$ to nitrogen (N $_{\rm 2}$).

In another aspect of the invention, it is an exhaust treatment system for nitrogen oxide reduction in lean burn engines comprising a non-thermal plasma in the exhaust system that is adapted to receive an

oxygen rich exhaust, the non-thermal plasma converting the nitrogen oxide (NO) and hydrocarbons in the oxygen rich exhaust into nitrogen dioxide (NO₂) and oxidized hydrocarbons, and a catalytic unit operably connected to the exhaust system and adapted to receive the oxygen rich exhaust after the non-thermal plasma, the catalytic unit comprising at least one metal doped Y-alumina, wherein the Y-alumina has a pore volume of at least 1.0 cubic centimeters per gram and the metal comprises indium, tin, gallium, silver, gold, copper, cobalt, iron, cerium, or mixtures thereof.

Brief Description of the Drawings

Fig. 1 is a block diagram of a machine embodiment of the present invention.

Fig. 2 shows the reduction of NO to $\ensuremath{N_2}$ over various alumina samples.

Fig. 3 shows the reduction of $N\text{O}_2$ to N_2 over the alumina samples used in Fig.2.

20 Fig. 4 shows the reduction of NO to N_2 over various catalyst samples.

Fig. 5 shows the reduction of NO_2 to N_2 over the various catalyst samples of Fig. 4.

Fig. 6 shows the reduction of NO to N_2 over indium doped Y-alumina at various indium levels.

Fig. 7 shows the reduction of NO_2 to N_2 over the indium doped ${\sf Y}\text{-alumina}$ samples of Fig. 6.

Fig 8 shows the reduction of NO to $\ensuremath{N_2}$ over tin doped Y-alumina at various tin levels.

Fig. 9 shows the reduction of NO_2 to N_2 over the tin doped Y-alumina samples of Fig. 8.

20

25

30

Fig 10 shows the reduction of NO to N_2 over gallium doped Y-alumina at various gallium levels. Fig. 11 shows the reduction of NO_2 to N_2 over the gallium doped Y-alumina samples of Fig. 10.

Fig. 12 shows the reduction of NO_x to N_2 in a plasma assisted catalytic system designed according to the present invention in the presence and absence of SO_2 .

10 Best Mode For Carrying Out The Invention

In Fig. 1 a block diagram of a machine embodiment of the present invention is shown generally at 10. A fuel tank 20 delivers fuel to a "lean burn" Throughout the specification and the engine 22. claims a lean burn engine is defined as one that produces an oxygen rich exhaust, which is defined as an exhaust having a higher molar ratio of oxygen than the total molar ratio of reductive compounds such as CO, hydrogen and hydrocarbons. The exhausts have an oxidative environment. Examples of such engines include diesel engines and various lean burn gasoline engines. Generally, these systems generate an exhaust having an oxygen content of from 4 to 16 % depending on the load conditions and the running mode of the engine. An oxygen rich exhaust exits engine 22 and is directed to pass through a non-thermal plasma 26. Preferably, this exhaust is supplemented, prior to treatment in the non-thermal plasma, by the addition of an atomized hydrocarbon or mixture of hydrocarbons 24. One source of these hydrocarbons can be the diesel fuel from the fuel tank 20. Alternatively, as

15

is known in the art, the supplemental hydrocarbon source can be other hydrocarbons other than the fuel.

Generation of a non-thermal plasma 26 is well known in the art and will not be described in In brief, a non-thermal plasma is created by detail. connecting an alternating current voltage source to a pair of spaced apart electrodes having a dielectric barrier located in the space between them. typical system one of the electrodes is formed by a rod located in the center of an exhaust tube and the exhaust tube forms the other electrode. Preferably the alternating current voltage source generates a current of approximately 10 to 30 kilovolts. Because of the speed of the cycling of the alternating current voltage an electron and ionized gas cloud is created in the space between the two electrodes. The nonthermal plasma in the presence of oxygen and hydrocarbons will convert NO_X into NO_2 plus oxygenated hydrocarbons such as alcohols, aldehydes, and ketones. This generates an intermediate exhaust, which contains NO_2 , oxygenated hydrocarbons, unreacted hydrocarbons, and oxygen. In the non-thermal plasma 26 up to 95% of the NO_x is converted to NO_2 .

The intermediate exhaust is directed to a catalytic unit 28. Deposited within the catalytic unit is a metal doped Y-alumina catalyst. The composition of this metal doped Y-alumina catalyst is described more fully below. In the catalytic unit 28 a substantial portion of the NO_2 is converted to the reaction products of N_2 , carbon dioxide, and water. The conversion products leave the catalytic unit as a cleaned exhaust 30.

15

20

25

30

Formation of Y-alumina by a sol gel procedure

It has been found in the present invention that Y-alumina formed by a sol gel method produces an alumina having unique properties for utilization in plasma-assisted catalysis (PAC) of oxygen rich exhaust. The Y-alumina was prepared by a complexing agent-assisted sol gel method.

In the sol gel method aluminum isopropoxide (AIP) (98+%, Aldrich Chemical Company, Inc.) was dissolved in 2-methyl-2,4-pentanediol (MPD) (99% Aldrich Chemical Company, Inc.). First, 500 g AIP was placed in a 2-liter glass beaker and then 600 milliliters of MPD was added immediately and the mixture was stirred vigorously with a mechanical polyethylene stirrer. Once the mixture was homogeneous, the beaker was placed in a constant temperature bath at a range of from 110 to 130°C and stirred continuously. After approximately 1 hour of stirring, all of the AIP was dissolved in the MPD. As the AIP reacts with the MPD, it produces 2-propanol which is released as a vapor at these temperatures. Gelation was completed after approximately 4 hours of Then 400 milliliters of water were added to reaction. stop the gelation and a white precipitate of aluminum hydroxide was obtained. The aluminum hydroxide solid was redispersed in water and aged at a temperature of from 60 to 90°C overnight with constant stirring.

After aging overnight, 600 milliliters of 2-propanol was added to remove the water from the pores of the precipitate. Although 2-propanol is preferred, any organic solvent having a surface tension of approximately equal to or less than 30 mN/m will be

useful. It is just necessary that the solvent have a surface tension significantly below that of water, which is approximately 72 mN/m. The resulting slurry was vacuum filtered and dried at approximately 90°C in an oven for 48 hours.

Calcination was carried out in a temperature programmed tube furnace with 5 L/min air flowing through it. A general calcination schedule is as follows: ramp the temperature from 100° C to 460° C at 1° C/min with air flowing through it; ramp the temperature from 460° C to 700° C at 1° C/min with 2% H_2 O/air; 2 hours at 700° C with 6% H_2 O/air; and turn off the heat and continue flowing air over the alumina until the temperature is reduced to 100° C.

This sol gel procedure resulted in Y-alumina (Al_2O_3) with a high surface area of approximately 200 to $230m^2/g$, a pore volume of from 1 to 2 cc/g, and a pore size of from 4 to 20 nm. Throughout the specification and claims the sol gel Y-alumina prepared according to the present invention was prepared as described above, the few exceptions are noted below.

Formation of metal doped Y-alumina

25 A metal doped Y-alumina prepared according to the present invention can be prepared in one of two ways. In one method, the subject metal is solubilized in the water that is used to stop gelation during the sol gel procedure described above. In a second

30 method, the sol gel Y-alumina is doped with a metal by an incipient wetness method. In this method, the sol gel Y-alumina is brought into contact with a solution

15

20

of the appropriate metal. The solution of the metal is present in an amount equal to or greater than the total pore volume of the Y-alumina sample. The pore volume of Y-alumina prepared according to the present invention is generally from 1.0 to 2.0 cubic centimeters per gram.

To form a tin doped Y-alumina by the incipient wetness method an appropriate amount of ${\rm SnCl_2}$ was dissolved in an ethanol solution and brought into contact with the sol gel Y-alumina. The tin doped Y-alumina catalyst was calcined at 600°C for 5 hours and then at 800°C for 2 hours.

An indium doped Y-alumina was prepared in the same manner using $In\,(NO_3)_3$ in a water solution instead of ethanol. The indium doped Y-alumina catalyst was calcined at 600°C for 5 hours.

A gallium doped Y-alumina was prepared by exposing the Y-alumina to a water solution of $Ga\,(NO_3)_3xH_2O$ which was added to the aluminum oxide gel during the Y-alumina preparation in the sol gel method. The gallium doped Y-alumina catalyst was calcined at 600°C for 5 hours.

Catalytic performance tests

Reactor bench tests to characterize the catalytic performance of various samples were performed in a quartz micro tube reactor with a feed gas of 0.1% NO_x , 0.1% propene, 15% O_2 , and 10% H_2O balanced with He. The flow rate was approximately 200 cc/min, and approximately 0.2 grams of catalyst was used. These conditions correspond to a space velocity

15

20

25

of $30,000h^{-1}$. The reaction products were analyzed by a gas chromatograph equipped with a 6' molecular sieve and a 6' Porapak Q column. The NO_x conversion was calculated from the amount of N_2 produced. No N_2O was detected in any of the experiments; thus, the N_2 yield corresponded to the NO_x conversion. The catalyst samples were pre-heated to $600\,^{\circ}$ C in a flow of O_2 and He. Then the samples were exposed to the oxygen rich simulated exhaust of $0.1\%~NO_x$, 0.1%~propene, $15\%~O_2$, and $10\%~H_2O$ balanced with He. In some experiments the level of oxygen varied, these changes are noted as appropriate below.

Surface area and pore volume measurements

The surface area, pore volume, and pore size distribution of various alumina samples were determined using a Micromeritics ASAP 2000 system. Approximately 0.2 to 2 grams of catalyst was out gassed under vacuum at $450\,^{\circ}\text{C}$ overnight prior to adsorption measurements. The surface area was determined by multipoints measurement using several relative pressures of N_2 to He in the range of 0.06 to 0.2 (N_2 surface area 0.162 nm²) at 77 K.

Impurity analysis of alumina samples

The level of the impurity sulfate (SO₄) in various alumina samples was determined using ICP analysis. The ICP analysis was performed using a Jobin Yvon 48 instrument. The alumina samples were completely digested in acid (HF) and diluted with deionized water. The acid solution was then injected

into the plasma and the instrument scanned the sample for all the elements including sulfur.

Thermal stability testing

The thermal stability of a Y-alumina prepared according to the above-referenced sol gel procedure was compared to various commercially available aluminas to determine whether its thermal stability were greater or less than these commercially available aluminas. To determine thermal stability surface area measurements for the various alumina samples were determined prior to and following hydrothermal aging tests. The aging test was 10 performed in a 6" in diameter tube furnace set at 800°C for 15 hours with a 10% $\rm H_2O/air$ flow at 5 liters per minute. The results of these tests are shown below in Table 1. The Y-alumina sample, prepared in accordance with the present invention, exhibited the 15 highest surface area following the hydrothermal testing and showed one of the lowest reductions in surface area. The Alcoa HiQ7214F showed the lowest surface area change, but this is believed to be due to its lower initial surface area. Thus, the Y-alumina 20 of the present invention is thermally more stable than

a number of commercial aluminas.

Table 1

Samples	Before	After	Surface Area		
	Aging	Aging	Change (%)		
	(m^2/g)	(m^2/g)			
Laroche (VGL-25)	280	146	48		
W.R. Grace	237	126	47		
(MI-200)		1			
Alcoa	160	102	36		
(DD447-165)					
Alcoa (HiQ7214F)	146	118	19		
Y-alumina	226	172	24		

Fig. 2 shows the NO reduction to N_2 over the various alumina samples disclosed in Table 1 above. The samples were exposed to a stream of 0.1% NO, 0.1% 5 propene, 15% $\mbox{O}_{2},\,\mbox{10% H}_{2}\mbox{O}$ at 200 cc/min at the indicated temperatures. The Y-axis is the percent conversion of ${\tt NO}$ to ${\tt N_2}$ and the X-axis is the stream temperature. Reference line 32 is the Y-alumina sample prepared by 10 the sol gel method; reference line 34 is the Grace MI-200 sample; and reference line 36 is the Alcoa DD447-165 sample. From Fig. 2 it can be seen that the Υ alumina prepared by the sol gel method shows both a higher maximum NO conversion and a broader temperature window than the commercial aluminas. In addition, the 15 Y-alumina sample showed higher NO conversion at lower temperatures.

In Fig. 3, the NO_2 reduction to N_2 over these same samples is shown. In this case the exposure was the same except that the NO was replaced with 0.1% NO_2 . Reference line 38 represents the Y-alumina prepared by

15

20

25

the sol gel method of the present invention; reference line 40 is the Grace MI-200 sample; and reference line 42 is the Aloca DD447-165 sample. As can be seen in Fig. 3, the Y-alumina also showed a higher NO_2

conversion than the commercial aluminas. The Υ -alumina also showed the lowest Tmax compared to the commercial aluminas.

The results shown in Figs. 2 and 3 indicate that the Y-alumina prepared by the sol gel method is more selective than commercial aluminas. By the term selective it is meant that the catalyst converts more NO_x to N_2 using less hydrocarbon. Also the Y-alumina converts NO_2 to N_2 to a higher extent than NO. This selectivity makes the sol gel Y-alumina particularly suitable for use in a PAC system.

Effect of alumina surface area, pore volume, pore size and sulfate impurity on the yield of N_2 from NO_2

Various alumina samples were obtained from commercial suppliers and in addition the sol gel method of the present invention was modified to generate Y-aluminas having a range of pore volumes.

The sample designated P091098 was prepared by the standard sol gel method with complexing agent as described above. Additional Y-aluminas according to the present invention were prepared with controlled pore structure without using a complexing agent. The procedure was to prepare a white slurry consisting of amorphous aluminum hydroxide by mixing aluminum isoproproxide with an excess of hot water at

isoproproxide with an excess of hot water at approximately 80°C under vigorous stirring conditions.

20

25

30

One-third of the slurry was washed with water and this sample was designated as P012299. Another third of the slurry was washed with 2-propanol and designated as P012299a. Washing with 2-propanol provided a

different surface tension on the Y-alumina during the drying step. Specifically because the surface tension of 2-propanol is smaller than water sample P012299a maintains its open pore structure resulting in a material containing a higher surface area, larger pore

volume and larger average pore size compared to the water-washed sample (P012299). To the final third of the slurry a small amount of nitric acid was added for peptization of the aluminum hydroxide to a clear sol. The clear sol solution was subsequently mixed with

15 500 milliliters of water. The redispersed sol solution was aged overnight at approximately 85°C. A glassy crystalline material was obtained and designated P012299b. This sample exhibited the smallest pore volume and the smallest pore size.

All of the Y-alumina samples prepared according to the present invention were dried at approximately 90°C overnight and calcined in a temperature-programmed furnace with a flowing air atmosphere. The furnace temperature was increased up to 700°C at a ramp rate of 1°C/min and held at 700°C for 2 hours.

The surface area, pore volume, and average pore size of all the samples were measured using BET measurement as described above. The impurity level of SO_4 was determined using ICP data as described above. Table 2 shows the results of the BET, ICP, and conversion of NO_2 to N_2 for the various alumina

25

samples. In Table 2 the samples are ranked according to their percent yield of N_2 from NO_2 . The top 8 samples have a sulfate impurity level of 0 with the exception of sample TA-1301E. This demonstrates the importance of reducing the sulfate impurity to obtain a catalytically active alumina. Of the top 8 aluminas shown in Table 2, the aluminas having larger pore volumes showed better NO_2 reduction activity than aluminas having relatively smaller pore volumes.

Among the top 3 aluminas shown in Table 2 the surface areas of these aluminas varied by a factor of 3, however the NO_2 reduction performances of these aluminas were comparable. Thus, the surface area does not seem to affect the catalytic activity of the alumina.

Based on these results it is preferred that any Y-alumina produced by any method used for the subject invention have a pore volume of from 1.0 to approximately 2.0 cubic centimeters per gram, and a sulfate impurity level of less than or equal to 0.1% sulfate. The surface area can vary, but it is preferable that it be equal to or greater than 200 m²/g. The Y-alumina can be prepared by any method such as precipitation in addition to the sol gel method so long as these physical characteristics are maintained. The results presented in Table 2 further reinforce the conclusion that the sol gel Y-alumina of the present invention is particularly suitable for use in a PAC system.

Table 2

						N ₂ Yield
				Average		from NO ₂
		Surface	Pore	Pore	i	Reduction
		Area	Volume	Size	Impurity	at 500°C
Rank	Samples	(m ² /g)	(cc/g)	(nm)	SO ₄ (%)	(%)
1	P091098	230	1.1	14	0.0	60
2	P012299a	380	1.8	14	0.0	53
3	TA-1301E [†]	120	1.1	30	0.6	53
4	Catalox°	150	0.49	9	0.0	52
5	Puralox°	160	0.68	15	0.0	51
6	P012299b	240	0.28	4	0.0	49
7	Dispal°	80	0.62	27	0.0	42
8	P012299	250	0.42	5	0.0	41
9	MI-200 [†]	260	0.84	9	0.15	40
10	TA-2301E [‡]	128	1.1	28	1.6	39
11	MI-307 HD [†]	270	0.70	8	0.31	37
12	MI-207 [†]	350	1.2	10	0.72	32
13	MI-307 [†]	170	0.77	14	0.2	27
14	MI-120 [†]	280	0.92	10	0.7	27
15	BK-112L [‡]	280	0.45	5	0.0	26
16	MI-407 [†]	160	0.72	14	0.16	26
17	BK-112 [‡]	320	0.2	3	0.0	23
18	MI-386 [†]	130	0.71	17	0.3	19

[†] W.R. Grace & Co., Columbia MD, USA; [‡] Sumitomo Chemical Company Limited, Niihama-shi Ehime-ken, Japan; and ^o Condea Vista Company, Austin TX, USA.

In Fig. 4 metal doped Y-alumina samples prepared according to the present invention were compared to other known standard catalysts for their ability to reduce NO to N_2 . All the samples were

15

20

25

exposed to a test gas of 0.1% NO, 0.1% propene, 9% O_{2} $7\ensuremath{\,^{\circ}}$ $H_2\ensuremath{\,^{\circ}}$ at 200 cc/min. Reference line 44 shows the activity of a Pt/Fe ceria doped titanium silicalite catalyst. Reference line 46 shows the activity of a standard Cu-ZSM5 catalyst. Reference line 48 shows a Y-alumina sample prepared by the sol gel method of the present invention and doped with 2.5 weight percent Reference line 50 shows the activity of a Yalumina sample prepared by the sol gel method of the present invention doped with 24 weight percent gallium. As can be seen from Fig. 4 metal doped Yalumina catalysts prepared according to the present invention are much more effective in reduction of NO than are either Pt or Cu-ZSM5 catalysts in reducing NO. Also the Pt catalyst produces a substantial amount of N_2O , which is a greenhouse gas.

In Fig. 5 the same samples as in Fig. 4 are shown for their ability to reduce NO_2 to N_2 . The reference lines 52-58 are, respectively, the Pt/Fe ceria doped titanium silicalite catalyst, Cu-ZSM5 catalyst, 2.5 weight % indium doped Y-alumina, and 24 weight % gallium doped Y-alumina. All the conditions are the same as for Fig. 4 except that the feed gas include 0.1% NO_2 instead of NO. Again, it can be seen that metal doped Y-alumina catalysts prepared according to the present invention yield more N2 than either Pt or Cu-ZSM5 catalysts. This selectivity makes the metal doped sol gel Y-alumina particularly suitable for use in a PAC system.

In Figs. 6 and 7, the effect of various doping levels of indium onto \mathbf{Y} -alumina prepared

according to the present invention is shown. metal doped Y-alumina samples were prepared as described above.

In Fig. 6 the ability of the various samples to reduce NO to N_2 is shown. The samples were exposed to a stream of 0.1% NO, 0.1% $C_3H_6,\ 9\mbox{\em O}_2,\ 7\mbox{\em H}_2\mbox{\em O},\ the$ balance being He. In Fig. 6, reference number 80 represents a non-doped Y-alumina prepared by the sol gel method; reference 82 represents a 1 weight percent indium doped Y-alumina; reference 84 represents a 2.5 10 weight percent indium doped Y-alumina; reference number 86 represents a 5 weight percent indium doped Y-alumina; and reference 88 represents a 10 weight percent indium doped Y-alumina.

15 In Fig. 7 the ability of the various samples to reduce NO_2 to N_2 is shown. The samples were exposed to a stream of 0.1% $\mathrm{NO_2}$, 0.1% $\mathrm{C_3H_6}$, 9% $\mathrm{O_2}$, 7% $\mathrm{H_2O}$, the balance being He. In Fig. 7, reference number 90 represents the non-metal doped Y-alumina; reference number 92 represents the 1 weight percent indium doped 20 Y-alumina; reference line 94 represents the 2.5 weight percent indium doped Y-alumina; reference 96 represents the 5 weight percent indium doped Yalumina; and reference 98 represents the 10 weight percent indium doped Y-alumina.

It can be seen from Figs. 6 and 7 that maximal activity was achieved with an indium level of approximately 2.5 weight percent. Furthermore, it can be seen that the indium doped Y-alumina catalyst

20

showed a lower Tmax and exhibited a broader temperature window than the pure Y-alumina itself.

In Figs. 8 and 9, a similar comparison was done for tin doped Y-alumina prepared according to the present invention. In Fig. 8, reference lines 100-112 represent, respectively, Y-alumina; 1 weight percent tin doped Y-alumina; 2.5 weight percent tin doped Yalumina; 5 weight percent tin doped Y-alumina; 10 weight percent tin doped Y-alumina; 15 weight percent tin doped Y-alumina; and 20 weight percent tin doped Y-alumina. In Fig. 9, reference numbers 114-126 represent, respectively, Y-alumina; 1 weight percent tin doped Y-alumina; 2.5 weight percent tin doped Yalumina; 5 weight percent tin doped Y-alumina; 10 weight percent tin doped Y-alumina; 15 weight percent tin doped Y-alumina; and 20 weight percent tin doped Y-alumina. In Fig. 8 the ability of the catalysts to reduce NO to $\ensuremath{\text{N}_{2}}$ is shown. In Fig. 9 the ability of the catalysts to reduce NO_2 to N_2 is shown. The results demonstrate that all of the tin doped Y-alumina catalysts show a lower Tmax and broader temperature window when compared to pure Y-alumina. The best performing tin doped Y-alumina was at approximately 10 weight percent.

In Figs. 10 and 11, a similar comparison was done for gallium doped Y-alumina prepared according to the present invention. Fig. 10 represents the reduction of NO to N_2 while Fig. 11 represents the reduction of NO_2 to N_2 In Fig. 10, reference numbers

15

20

30

128-140 represent, respectively, non-metal doped Yalumina; 1 weight percent gallium doped Y-alumina; 2.5 weight percent gallium doped Y-alumina; 6 weight percent gallium doped Y-alumina; 10 weight percent gallium doped Y-alumina; 20 weight percent gallium doped Y-alumina; and 24 weight percent gallium doped Y-alumina. In Fig. 11 reference numbers 142-154 represent, respectively, non-metal doped Y-alumina; 1 weight percent gallium doped Y-alumina; 2.5 weight percent gallium doped Y-alumina; 6 weight percent gallium doped Y-alumina; 10 weight percent gallium doped Y-alumina; 20 weight percent gallium doped Yalumina; and 24 weight percent gallium doped Y-In addition to the samples shown in Figs. 10 alumina. and 11, a 50 weight percent gallium doped Y-alumina sample has been prepared. 50 weight percent gallium doped Y-alumina shows the highest activity for NO or ${\rm NO}_2$ reduction. All of the gallium doped Y-alumina catalysts show better activity than the Y-alumina catalyst alone and show a wider temperature window. All of the metal doped catalysts showed more $\mathtt{NO_x}$ reduction when NO was replaced with NO_2 making these good catalysts for a PAC system.

The performance of a PAC system for lean NO_x reaction

To assess the impact of a non-thermal plasma on metal doped Y-alumina catalysts prepared according to the present invention, a simulated exhaust system was designed by coupling a non-thermal plasma in a

tube to a catalytic unit in a standard two-stage setup to form a PAC system. The catalytic unit comprised a quartz tube that was packed with catalyst powder. The catalyst is held in place with quartz wool and fritted quartz disks. A 1 L/min gas flow was used in combination with 1 gram of catalyst powder. This results in a space velocity of 30,000 hr⁻¹ depending on the powder used. The simulated oxygen rich exhaust was composed of 500 ppm NO, 300 ppm CO, 8% CO_2 , 1,5% H_2O , 9% O_2 , 2000 ppm propene, plus or minus 20 ppm SO_2 , and the balance N_2 .

In Fig. 12 the data were obtained using a 2.5 weight % indium doped Y-alumina prepared by the sol gel method are shown. In Fig. 12 the Y-axis is the percentage of the NO in the simulated exhaust that 15 was converted to N_2 and the X-axis is the energy deposited by the non-thermal plasma. The results are shown for with or without SO_2 at tempertures of 200° C, 350° C, and 500° C. Reference lines 172 and 174 represent with and without SO₂ at 200° C, respectively. 20 Reference lines 176 and 178 represent with and without SO_2 at 350° C, respectively. Reference lines 180 and 182 represent with and without SO_2 at 500° C, respectively. The catalytic activity of the indium doped Y-alumina was reduced by the presence of the SO_2 . 25 At tempertures near that of normal exhaust, between 350° C and 500° C, the coversion by the indium doped Y-alumina was very high with or without SO_2 . At a temperature of 500° C the coversion in the absence of SO_2 was 90% while the coversion in the presence of SO_2 30 was 80%. Even in the presence of SO_2 the conversion

was very high compared to other presently known lean $\ensuremath{\text{NO}_{x}}$ catalyst systems.

In addition to the metals that have been disclosed above for doping of the Y-alumina prepared by the sol gel method, other metals that could be utilized include silver, gold, copper, cobalt, iron, and cerium. In practicing the present invention the Y-alumina preferably has a pore volume of from about 1.0 to about 2.0 cubic centimeters per gram, a surface area of greater than or equal to 200 meters squared per gram, and a sulfate level of less than or equal to 0.1%. In a preferred embodiment the Y-alumina is prepared by a sol gel method.

Of course, various modifications of this invention would come within the scope of the invention.

Industrial Applicability

The present invention is utilized for the 20 treatment of oxygen rich exhaust. In one use, the present invention is utilized to remove nitrogen oxides from diesel engine exhaust. In a first step the diesel engine exhaust is passed through a nonthermal plasma generated by conventional means. Prior to passing through the non-thermal plasma preferably 25 the diesel exhaust is supplemented with additional hydrocarbons, which can comprise diesel fuel itself. In this first step, up to 95% of the nitrogen oxide in the oxygen rich exhaust is converted into nitrogen dioxide and the hydrocarbons are oxidized thereby 30 forming an intermediate exhaust rich in nitrogen dioxide. The intermediate exhaust is passed over at

least one metal doped Y-alumina wherein the Y-alumina has a pore size of greater than or equal to 1.0 cubic centimeter per gram. The metal doped Y-alumina converts the nitrogen dioxide to N_2 . The present invention finds utilization as a method for treating any oxygen rich exhaust such as diesel or lean burn gasoline engine exhaust.

Other aspects, objects and advantages of this invention can be obtained from a study of the drawings, the disclosure and the appended claims.

15

20

25

Claims

- 1. A method for nitrogen oxide (NO_x) reduction in an oxygen rich engine exhaust comprising the steps of:
 - a) passing an oxygen rich exhaust through a non-thermal plasma thereby converting nitrogen oxide (NO) and hydrocarbons in the oxygen rich exhaust into nitrogen dioxide (NO $_2$) and oxidized hydrocarbons and forming an intermediate exhaust;
 - b) passing the intermediate exhaust over at least one metal doped Y-alumina, wherein the Y-alumina has a pore volume of at least 1.0 cubic centimeter pre gram, thereby converting the NO_2 to nitrogen (N_2) .
- 2. A method as claimed in Claim 1, wherein step a) comprises the further step of injecting an amount of at least one atomized hydrocarbon into the oxygen rich exhaust prior to passing the oxygen rich exhaust through the non-thermal plasma.
- 3. A method as recited in Claim 1, wherein step a) further comprises passing an oxygen rich exhaust having an oxygen content of equal to or greater than 4% through the non-thermal plasma.
- 4. A method as recited in Claim 1, wherein step b) further comprises a step of selecting the

 30 metal for doping of the Y-alumina from the group consisting of indium, tin, gallium, silver, gold, copper, cobalt, iron, cerium, and mixtures thereof.

- 5. A method as recited in Claim 1, wherein step b) comprises a further step of doping the Y-alumina with the metal by incorporating the metal into water used for a gelation step as part of a sol gel method for formation of the Y-alumina.
- 6. A method as recited in Claim 1, wherein step b) comprises a further step of doping the Y-alumina with the metal by bringing the Y-alumina into contact with a solution of the metal wherein the solution of the metal is present in an amount equal to or greater than the total pore volume of the Y-alumina.
- 7. A method as recited in Claim 1, wherein step b) comprises a further step of doping the Y-alumina with from about 1 weight percent to about 10 weight percent indium.
- 8. A method as recited in Claim 1, wherein step b) comprises a further step of doping the Y-alumina with from about 1 weight percent to about 20 weight percent tin.
- 9. A method as recited in Claim 1, wherein step b) comprises a further step of doping the Y-alumina with from about 1 weight percent to about 55 weight percent gallium.

20

25

- 10. A method as recited in Claim 1, wherein step b) comprises a further step of preparing the Υ -alumina by a sol gel method.
- 5 11. A method as recited in Claim 1, wherein step a) further comprises a step of passing a diesel exhaust through the non-thermal plasma thereby converting the nitrogen oxide (NO) and hydrocarbons in the diesel exhaust into nitrogen dioxide (NO₂) and 10 oxidized hydrocarbons and forming an intermediate exhaust
 - 12. An exhaust treatment system for nitrogen oxide reduction in lean burn engines comprising:

a non-thermal plasma in an exhaust system that is adapted to receive an oxygen rich exhaust, said non-thermal plasma converting the nitrogen oxide (NO) and hydrocarbons in said oxygen rich exhaust into nitrogen dioxide (NO_2) and oxidized hydrocarbons;

a catalytic unit operably connected to said non-thermal plasma and adapted to receive said oxygen rich exhaust after said non-thermal plasma, said catalytic unit comprising at least one metal doped Y-alumina, wherein said Y-alumina has a pore volume of at least 1.0 cubic centimeters per gram and said metal comprises indium, tin, gallium, silver, gold, copper, cobalt, iron, cerium, or mixtures thereof.

 30 13. A system as recited in Claim 12, wherein said Y-alumina is doped with from about 1 weight percent to about 10 weight percent indium.

- 14. A system as recited in Claim 12, wherein said Y-alumina is doped with from about 1 weight percent to about 20 weight percent tin.
- 5 15. A system as recited in Claim 12, wherein said Y-alumina is doped with from about 1 weight percent to about 55 weight percent gallium.
- 16. A system as recited in Claim 12,10 wherein said Y-alumina has a pore volume of from 1.0 to 2.0 cubic centimeters per gram.
- 17. A system as recited in Claim 12, wherein said Y-alumina has a sulfate content of less than or equal to 0.1 weight percent.
- 18. A system as recited in Claim 12, wherein said Y-alumina is doped with a metal comprising either 2.5 weight percent indium, 10 weight percent tin, 50 weight percent gallium, or mixtures comprising indium, tin, and gallium.
- 19. A system as recited in Claim 12, wherein said Y-alumina has a surface area of at least 25 200 meters squared per gram.
 - $$20.\,$ A system as recited in Claim 12, wherein said $Y\mbox{-alumina}$ is doped with mixtures of metals comprising indium, tin, and gallium.

10

15

20

Abstract of the Disclosure

METHOD AND SYSTEM FOR THE COMBINATION OF NON-THERMAL PLASMA AND METAL/METAL OXIDE DOPED Y-ALUMINA CATALYSTS FOR DIESEL ENGINE EXHAUST AFTERTREATMENT SYSTEM

The present disclosure pertains to a system and method for treatment of oxygen rich exhaust and more specifically to a method and system that combines non-thermal plasma with a metal doped Y-alumina catalyst. Current catalyst systems for the treatment of oxygen rich exhaust are capable of achieving only approximately 7 to 12% NO_x reduction as a passive system and only 25-40% reduction when a supplemental hydrocarbon reductant is injected into the exhaust It has been found that treatment of an oxygen stream. rich exhaust initially with a non-thermal plasma and followed by subsequent treatment with a metal doped Yalumina prepared by the sol gel method is capable of increasing the NO_x reduction to a level of approximately 90% in the absence of SO2 and 80% in the presence of 20 ppm of SO2. Especially useful metals have been found to be indium, gallium, and tin.




Fig. 1

